

# CARBOREX NG 2-9

## BLACK NARROW SILICON CARBIDE MICRO GRITS

FOR SPECIAL APPLICATIONS

### Silicon Carbide Inquiries

#### Norway

Tel: +47-72-48-35-00  
wmas@washingtonmills.no

#### General Inquiries

##### Europe

Tel: +44(0)161-848-0271  
info@washingtonmills.com

##### North & South America

Tel: 1-800-828-1666  
info@washingtonmills.com

### Washington Mills AS

NO-7300  
Orkanger, Norway  
Email: wmas@washingtonmills.no  
Tel: +47-72-48-35-00  
Fax: +47-72-48-35-01  
wmas@washingtonmills.no

### Washington Mills

**North Grafton, Inc.**  
P.O Box 428  
20 North Main Street  
North Grafton, MA 01536  
Tel: 508-839-6511  
Fax: 508-839-7675  
info@washingtonmills.com

### Washington Mills Electro Minerals Corp.

P.O Box 423  
1801 Buffalo Avenue  
Niagara Falls, NY 14302  
Tel: 716-278-6600  
Fax: 716-278-6650  
info@washingtonmills.com

### Washington Mills Electro Minerals Corp.

P.O Box 1002  
7780 Stanley Avenue  
Niagara Falls, Ontario  
L2E 6V9 Canada  
info@washingtonmills.com

### Washington Mills

**Tonawanda, Inc.**  
1000 E. Niagara Street  
Tonawanda, NY 14150  
info@washingtonmills.com

### Washington Mills Electro Minerals Ltd.

Mosley Road, Trafford Park  
Manchester M17 1NR England  
info@washingtonmills.com

### Washington Mills Hennepin, Inc.

13230 Prairie Industrial Parkway  
Hennepin, IL 61327  
info@washingtonmills.com





**CARBOREX NG SILICON CARBIDE** is an exceptionally narrow grit with high density, and good flow properties for special applications.

### PARTICLE SIZE DISTRIBUTION

| Product | D50<br>$\mu\text{m}$ | Range d3-d95<br>$\mu\text{m}$ | TD Typical<br>$\text{g}/\text{cm}^3$ |
|---------|----------------------|-------------------------------|--------------------------------------|
| NG 9    | 9,0 $\pm$ 0,4        | 5,0                           | 1,8                                  |
| NG 7    | 7,0 $\pm$ 0,4        | 4,5                           | 1,7                                  |
| NG 5    | 5,0 $\pm$ 0,4        | 4,0                           | 1,7                                  |
| NG 4    | 4,0 $\pm$ 0,4        | 4,0                           | 1,6                                  |
| NG 3    | 3,0 $\pm$ 0,4        | 3,5                           | 1,4                                  |
| NG 2    | 2,0 $\pm$ 0,4        | 3,5                           | 1,2                                  |

More sizes are under development. Particle size distribution measured on Beckman Coulter Multisizer.

### NG 9 VS. P1500



This product information is NOT a specification. It is offered in good faith only as a general description of the product. Washington Mills makes no warranty of merchantability or of fitness for any particular purpose. The product chemistry and other characteristics may vary or contain trace elements not specifically listed. If your intended application for this product is so critical that relatively minor variations in chemistry or physical properties could cause problems or damage to your process or product, please contact our office for further assistance.